

DICOR WHITE ACRYLIC ROOF COATING

1. Using the masking tape provided, mask off roof edging to enable COATING to be applied with a clean, straight edge. Also, mask other surfaces where you do not want COATING to be applied.
2. DICOR WHITE ACRYLIC COATING must be preceded with DICOR EPDM CLEANER / ACTIVATOR to ensure proper adhesion (See Cleaner / Activator application). Cleaner / Activator must be removed by power washing prior to application of ACRYLIC COATING.
3. All surfaces must be clean and free of residue or loose particles, degraded substrate, grease, oil, dirt, or other contaminants. Surfaces shall be completely dry and frost-free before coating.
4. DICOR WHITE ACRYLIC COATING shall be applied in a minimum of a 2 coats at a rate of 1 gallon per 125 sq. ft. per coat (i.e., 8'X30' roof takes 4 gallons). Actual gallons required will depend on the type of surface and texture, method of application, and weather conditions at the time of application. All surfaces must be uniformly coated and free from voids, pinholes, or blisters.
5. Thoroughly mix the contents for a minimum of 5 minutes prior to application. DICOR WHITE ACRYLIC COATING may be applied by roller (provided) or brush. DICOR WHITE ACRYLIC COATING shall be applied in a minimum of 2 coats at a rate of 1 gallon per 125 sq. ft. per coat (i.e., 8'X30' roof takes 4 gallons).
6. Allow to dry for 12 to 24 hours depending on weather conditions.



DICOR CORPORATION
52878 AIRPORT PARKWAY
ELKHART, IN 46514

Tele: (574) 264-2699
Fax: (574) 293-2017
Internet: www.dicor.com



VG 7.24.09



Roof Renew Kit APPLICATION INSTRUCTIONS

*Put the Beauty Back in Your RV's Rubber Roof
and
Add Years to its Life*

Note: The enclosed products are designed to work together as a system. * ENTIRE PROJECT MUST BE COMPLETED IN ONE DAY: INCLUDING CLEANER / ACTIVATOR APPLICATION, RINSING AND 2 COATS OF ACRYLIC COATING, EACH DRY TO THE TOUCH.

Contents: 4 - One Gallon Pails Dicor White Acrylic Roof Coating
2 - Quarts Dicor Cleaner / Activator
1 - 4" x 50' Roll Coating Ready Cover Tape
1 - Metal Pan
1 - 9" Paint Roller
2 - 9" Roller Covers
1 - Roll 1" Masking Tape
1 - Set Detailed Application Instructions

Kit contents will cover a 30 Ft. unit. Additional quantities of Cleaner / Activator and Dicor Acrylic Coating can be purchased separately to accommodate larger units.

Backed by Manufacturer's 5-year Limited Warranty*

* Please read directions for application on each product label. Dicor is not responsible for consequences of improper application.

SURFACE INSPECTION AND PREPARATION

1. Remove heavy deposits of dirt, leaves, pine needles and other debris using a broom or air blower. Any rocks or other large objects should also be removed.
2. Roof must be in good condition. Do not apply on pryable or brittle roofing. EPDM surface must be free of standing water, ice, snow, oils or grease at time of application.
3. Inspect roof carefully for cracks in the surface. These will need to be repaired later (see Coating Ready Cover Tape).
4. EPDM CLEANER / ACTIVATOR is designed for use on rubber roofing surface only and may damage other exterior parts of RV. It is highly recommended that you secure plastic sheeting over entire sidewalls as well as front and rear end caps to protect them from possible damage. If EPDM CLEANER / ACTIVATOR contacts any surface other than roof, it should be rinsed immediately.

DICOR CLEANER / ACTIVATOR APPLICATION

1. **DANGER: MAY CAUSE SEVERE IRRITATION OF THE EYES AND SKIN, GASTROINTESTINAL IRRITATION, NAUSEA, VOMITING AND DIARRHEA. MAY BURN MOST SKIN.**
Prolonged or repeated breathing of vapor or spray mist may be harmful. Use a respirator for protection from vapor or spray mist. Wear chemical resistant gloves, splash proof goggles and rubber overshoes. Avoid eye and skin contact. Do not take internally. Wash thoroughly after handling and before eating or smoking. Keep container closed when not in use.
2. EPDM CLEANER / ACTIVATOR is a ready-to-use material. It can be applied using a Hudson-type agricultural sprayer. Safety glasses with side shields and latex gloves are recommended when transferring EPDM CLEANER / ACTIVATOR from the shipping container to the sprayer. Spray a fine mist that leaves roof damp. Adjust spray for weather conditions if necessary. If EPDM CLEANER / ACTIVATOR is running off roof, you have used too much. If using a Hudson sprayer, adjust the spray

nozzle to achieve a uniform spray pattern with a 3 to 4 foot arc. Application rate is 125 sq. ft. per quart over new or existing surfaces. Do not apply below 40 degrees F (4 degrees C).

3. Allow EPDM CLEANER / ACTIVATOR to stand a minimum of 5 minutes to wet out and react with the EPDM surface. For best results, rinse with clean water using a minimum 2,000 psi pressure washer. Begin the power rinse at the lowest point on the roof and work upwards, keeping the pressure washer tip within 12" of the EPDM surface. Once the highest point on the roof is reached, work down again with a final rinse to remove any excess dirt or debris from the roof. After cleaning, the roof should be "white" in color, which is an indication that the surface has been chemically altered. Allow surfaces to dry thoroughly prior to application of two coats of the DICOR WHITE ACRYLIC COATING
4. Clean equipment with water and biodegradable detergent. Purge the water from the pump and hoses using Mineral Spirits prior to storing for any length of time.

COATING READY COVER TAPE

1. Roof must be cleaned with CLEANER / ACTIVATOR prior to application of COATING READY COVER TAPE.
2. Any areas that are torn or cracked may now be repaired using the COATING READY COVER TAPE.
3. Peel off a few inches of the release liner and carefully position the COATING READY COVER TAPE before applying. Any attempt to reposition the tape after application will damage the material.
4. Apply pressure starting at the center of the tape and working towards the outside edges, removing any bubbles as you go. When finished, the edges should have no tunnels, openings or fishmouths.
5. Only apply COATING READY COVER TAPE to areas that are to be coated the same day.